



MATERIAL TEMPERATURE COMPARISONS

NOMINAL TEMPERATURE RANGE/INSULATING AND JACKETING COMPOUNDS				
Compound	Normal Low	Normal High	Special Low	Special High
Chlorosulfonated Polyethylene (Hypalon*)	-20	90	-40	105
EPDM (Ethylene-Propylene-Diene Monomer)	-55	105	-	150
Neoprene	-20	60	-55	90
Polyethylene (Solid and Cellular)	-60	80	-	-
Polypropylene (Solid and Cellular)	-10	105	-	-
Rubber (EPR, Hypalon)	-30	60	-55	75
FEP Teflon*	-70	200	-	-
PVC	-20	80	-55	150
Silicone**	-80	150	-	200
Halar***	-70	150	-	-
Tefzel*	-65	150	-	-
TFE Teflon (Harsher Environments)	-70	260	-	-

*DuPont Trademark

** General Electric TradeMark

*** Ausimont Corporation Trademark



Technical Reference